



中国认可
国际互认
检测
TESTING
CNAS L4743

Test Report

Report No.: AJFS2403001956FF

Date: MAR.19, 2024

Page 1 of 5

B3012, DONGCHANG EAST ROAD, LIAOCHENG CITY, SHANDONG PROVINCE, CHINA

Sample Description: SPC FLOORING

SGS Ref No.: QDIN2402000316PL01

Style/Item No.: /

Spec.: SIZE: 1220*228*5mm

WEAR-LAYER THICKNESS 0.3mm

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Test Requested:

EN 13501-1:2018 Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests.

Test Results: -- See attached sheet --

Test Period:

Sample Receiving Date : MAR.04, 2024

Test Performing Date : MAR.04, 2024 TO MAR.15, 2024

Signed for and on behalf of

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch

Echo Li

Approved Signatory

Scan to see the report



AJFS2403001956FF
Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Test Report

Report No.: AJFS2403001956FF

Date: MAR.19, 2024

Page 2 of 5

I. Test conducted

This test was conducted as per EN 13501-1:2018 Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests. And the test methods as following:

1. EN ISO 9239-1:2010 Reaction to fire tests for floorings —Part 1: Determination of the burning behaviour using a radiant heat source.
2. EN ISO 11925-2:2020 Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test.

II. Details of classified product

Sample description	SPC flooring (provided by client)
Color	Wood color
Sample Size	EN ISO 9239-1: 1050mm×230mm EN ISO 11925-2: 250mm×90mm
Thickness	5.0mm
Mass per unit area	10.4 kg/m ²
Exposed surface	Front surface

Mounting and fixing:

Fibre cement board, with its density approximate 1800kg/m³, thickness approximate 9mm, is as the substrate. The test specimens are fixed mechanically to the substrate. Have joints in the specimens.

III. Test results

Test methods	Parameter	Number of tests	Results
EN ISO 9239-1	Critical flux (kW/m ²)	3	≥ 11.0
	Smoke (%×minutes)		20.6
EN ISO 11925-2 Exposure = 15 s	Whether vertical flame spread (Fs) in excess of 150 mm within 20 s (Yes/No)	6	No



IV. Classification and direct field of application

a) Reference of classification

This classification has been carried out in accordance with **EN 13501-1:2018**.

b) Classification

The product, SPC flooring (provided by client), in relation to its reaction to fire behaviour is classified:

Fire behaviour		Smoke production	
B _{fl}	—	s	1

Reaction to fire classification: B_{fl}—s1

Remark: The classes with their corresponding fire performance are given in annex A.

c) Field of application

This classification is valid for the following end use applications:

- With all substrates classified as A1 or A2
- With mechanically fixing
- Have joint

This classification is valid for the following product parameters:

- Characteristics as described in section II of this test report.

Statement:

This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Warning:

This classification report does not represent type approval or certification of the product.

The test laboratory has, therefore, play no part in sampling the product for the test, although it holds appropriate references to the manufacturer's factory production control that is aimed to be relevant to the samples tested and that will provide for their traceability.



Test Report

Report No.: AJFS2403001956FF

Date: MAR.19, 2024

Page 4 of 5

Annex A

Classes of reaction to fire performance for floorings

Class	Test methods	Classification	Additional classification
A _{1fl}	EN ISO 1182 ^a and	$\Delta T \leq 30^{\circ}\text{C}$, $\Delta m \leq 50\%$, $t_f = 0$ (i.e. no sustained flaming)	-
	EN ISO 1716	$\text{PCS} \leq 0.0\text{MJ/kg}$ ^a $\text{PCS} \leq 0.0\text{MJ/kg}$ ^b $\text{PCS} \leq 1.4\text{MJ/m}^2$ ^c $\text{PCS} \leq 0.0\text{MJ/kg}$ ^d	-
A _{2fl}	EN ISO 1182 ^a or	$\Delta T \leq 50^{\circ}\text{C}$, $\Delta m \leq 50\%$, $t_f \leq 20\text{s}$	-
	EN ISO 1716 and	$\text{PCS} \leq 3.0\text{MJ/kg}$ ^a $\text{PCS} \leq 4.0\text{MJ/m}^2$ ^b $\text{PCS} \leq 4.0\text{MJ/m}^2$ ^c $\text{PCS} \leq 3.0\text{MJ/kg}$ ^d	-
	EN ISO 9239-1 ^e	Critical flux ^f $\geq 8.0\text{kW/m}^2$	Smoke production ^g
B _{fl}	EN ISO 9239-1 ^e and	Critical flux ^f $\geq 8.0\text{kW/m}^2$	Smoke production ^g
	EN ISO 11925-2 ^h Exposure = 15s	$F_s \leq 150\text{mm}$ within 20 s	-
C _{fl}	EN ISO 9239-1 ^e and	Critical flux ^f $\geq 4.5\text{kW/m}^2$	Smoke production ^g
	EN ISO 11925-2 ^h Exposure = 15s	$F_s \leq 150\text{mm}$ within 20 s	-
D _{fl}	EN ISO 9239-1 ^e and	Critical flux ^f $\geq 3.0\text{kW/m}^2$	Smoke production ^g
	EN ISO 11925-2 ^h Exposure = 15s	$F_s \leq 150\text{mm}$ within 20 s	-
E _{fl}	EN ISO 11925-2 ^h Exposure = 15s	$F_s \leq 150\text{mm}$ within 20 s	-
F _{fl}	EN ISO 11925-2 ^h Exposure = 15s	$F_s > 150\text{mm}$ within 20 s	-

^a For homogeneous products and substantial components of non-homogeneous products.

^b For any external non-substantial component of non-homogeneous products.

^c For any internal non-substantial component of non-homogeneous products.

^d For the product as a whole.

^e Test duration = 30 min.

^f Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame).

^g s1 = Smoke $\leq 750\%$ minutes;

s2 = not s1.

^h Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack.



Test Report

Report No.: AJFS2403001956FF

Date: MAR.19, 2024

Page 5 of 5

Photo Appendix:



SGS authenticate the photo on original report only

End of Report